

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMONDS AND COLORED STONES **EDUCATIONAL PROGRAMS**

> Expertise issued by I.G.I. b.v.b.a Head Office and Laboratories.

1/7 Schupstraat, 2018 Antwerp - Belgium Tel. (32-3) 231 68 45 (6 L.) - Fax. (32-3) 232 07 58

Number: F2C76428

LABORATORY REPORT (ORIGINAL)

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information about the submitted stone.

ANTWERP, 12 OCT 1994

TO WHOM IT MAY CONCERN.

DESCRIPTION:

NATURAL DIAMOND

SHAPE AND CUT:

ROUND BRILLIANT

WEIGHT:

1.08 Carat

MEASUREMENTS:

6.47 - 6.58 x 4.08mm

PROPORTIONS and FINISH

Table Diameter Percentage

62.5 %

Crown Height Percentage

16 %

Pavilion Depth Percentage

44 %

CULFT SIZE:

MEDIUM

GIRDLETHICKNESS:

THIN TO MEDIUM (FACETED)

FINISH: Polish/Sym & Prop

VERY GOOD / VERY GOOD

COLOR GRADE:

NATURAL FANCY


BROWNISH ORANGE


FLUORESCENCE:

SLIGHT

The symbols do not usually reflect the size of the characteristics.

Red symbols indicate internal characteristics. Green symbols indicate external characteristics.





COMMENTS:

(insignificant external details, visible under high magnification, are not mentioned)

Control Department

LABORATORY DIRECTOR, GEMMOLOGIST

si 2

pl

02

p3

SPACE FOR DOUBLE CHECK, CLARITY AND COLOR GRADE

CLARITY GRADE Internally Flawless

vvs 1 vvs 2 vs 1 vs 2 si 1

10 11 12 13 COLOR GRADE: OP M 0 20 D N

PROPORTIONS - MARGIN: ± 1%.
MEASUREMENTS - MARGIN: ± 0.02 mm.

The gemmological analysis of diamonds, precious stones and other minerals must be carried out by specialized gemmologists with many years' experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic stones, as well as various treatment methods currently encountered are all very important factors

More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects

involved in the cutting process are essential.

Definition of a stone's color requires knowledge of type Ia, Ib, IIa and IIb diamonds, and correct use of masterstones and other relevant techniques. In order to grade the clarity of a diamond, the nature, number, size and location of any inclusions as well as any other secondary external characteristics must be determined.

This report is subject to the terms and conditions set forth on reverse.